

# Marlow®

## DATASHEET

### DYNALINE



Dynaline is made with high strength, light weight UHMPE (Dyneema®) fibre and is designed to replace steel wire winch ropes on 4x4's and recovery vehicles. Dynaline enables significantly quicker and safer deployment and recovery than traditional steel wire ropes, virtually eliminating dangerous recoil if fittings or attachments fail or in the unlikely event of rope failure.

#### APPLICATIONS:

Winching

#### MATERIAL:

UHMPE (High-Modulus Polyethylene) Dyneema®

#### BENEFITS:

Very light weight – 8x lighter than steel wire for a given strength.  
High strength - 70% stronger than steel wire for a given diameter.  
Low Stretch – see graph below.  
Good resistance to chemicals and UV.  
Zero water shrinkage.

#### CONSTRUCTION

##### TWISTED FIBRE CONSTRUCTION:

Improved abrasion resistance

##### 12 STRAND BRAIDED CONSTRUCTION:

Optimised pitch to yarn twist - improves strength & longevity.  
Firmer round rope, aids handling.  
Easy to splice.  
Flexible product and easily handled.  
Torque balanced.

##### HEAT SET AND PRE-STRETCHED:

Maximises strength/diameter ratio.  
Minimises elongation.

#### COATING

##### MARLOW ARMOURCOAT:

Specially formulated polyurethane coating.  
Improves abrasion resistance and durability.  
Increases friction, aids handling & splicing.  
Provides colour coding (black as standard, other colour options available on request).

#### PHYSICAL PROPERTIES

##### RELATIVE DENSITY:

0.97 (floats).

##### CHEMICAL RESISTANCE:

Excellent resistance to most chemicals (additional information available).

##### UV RESISTANCE:

Very good.

##### MELTING POINT:

140°C.

##### CRITICAL TEMPERATURE:

80°C.

## TERMINATIONS

### SPLICED EYE TERMINATION:

- 12 strand splice
- An allowance of 60x rope diameter should be made for the overall length of the splice.
- To optimise the efficiency of a soft eye splice (without a thimble), the angle formed at the neck of the splice should be 30° or less, meaning that when flat, the length of the eye must be 2.7x the diameter of the object over which the splice will be used.
- A splice will normally increase the diameter of the rope between 1.5x and 1.75x.



DIAMETER		CIRCUMFERENCE		MASS		AVERAGE STRENGTH			MIN STRENGTH		
mm	Inch	g/m	lb/100 ft	kg	lb	kN	kg	lb	kN		
6	7/32	16.0	1.07	3130	6900	30.7	2880	6350	28.3		
8	5/16	30.9	2.07	6340	14000	62.2	5830	12900	57.2		
9	23/64	38.0	2.55	7640	16800	75.0	7030	15500	69.0		
10	13/32	48.6	3.26	9530	21000	93.5	8770	19300	86.0		
11	7/16	57.1	3.83	11700	25800	114.9	10800	23800	105.7		
12	15/32	66.4	4.45	13400	29500	131.4	12300	27200	120.9		

**N.B.** AVERAGE AND MINIMUM STRENGTH DETAILED BELOW IS FROM A SPLICED CONDITION AS TESTED AND AS TERMINATED IN USE.

Marlow Ropes Ltd  
Ropemaker Park  
Hailsham  
East Sussex, BN27 3GU  
England

Marlow Ropes, Inc.  
Cordage Business Park  
Plymouth  
MA 02360  
USA

www.marlowropes.com  
UK: +44 (0) 1323 444 444  
sales@marlowropes.com  
US: +1 508 830 444  
salesusa@marlowropes.com



#### Disclaimer

Marlow Ropes Ltd endeavours to ensure that all products are manufactured to the highest standard, these guidelines are not intended and do not create any warranties, express or implied. Marlow Ropes Ltd expressly disclaims warranties or representations of any kind, express or implied, including the implied warranties of merchantability and fitness for a particular purpose. Marlow Ropes Ltd shall not be liable for any consequential, incidental or contingent damages whatsoever stemming from the use of these guidelines. Marlow Ropes Ltd has a policy of continual improvement which may result in specification and colour changes without prior notice.